



BODY 697 SR PROLINE 2:1 CLEAR COAT

Technical Data Sheet No 216

High solid clear coat suitable for full body repairs or spot panel repairs

Great gloss retaining

Excellent mechanical and high chemical resistance

Excellent physical properties

General Technical Description



Mix 2:1 with BODY 620 ECONOMY PROLINE HARDENER

Thinner addition 0-10% BODY 740 ACRYLIC THINNER

Oven force drying
20-30 min / 60-65°C
panel temperature



IR drying 8-10 min
distance 60 - 70 cm

Surface

Body Basecoat

Body 2K Autoemail acrylic paint

Aqua Body Waterbone mix system

Pretreatment / Cleaning of substrate



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL / BODY 771 ANTISIL FAST

Make sure the surface is air dried rather than wiped dry



Make sure you always use appropriate face protection and good ventilation

Product Application: 2 passes »» Apply one hand, and after the 10 min flash off time apply the second full hand.



2:1 mix with BODY 620 ECONOMY PROLINE HARDENER
Pot life: > 7h 23°C



10 min / 20-22°C
Final flash off time

Flash Point:
24°C / 52°F

Specific Gravity:
0.955 g/cm³

Remarks:

- Allow for additional time for combi spray booths to reach the desired temperature
- Application only with BODY 722 FAST HARDENER
- It can only be used by countries that do not adopt the VOC legislation
- Guaranteed shelf life of 24 months in unused original containers



Addition 0-10% of thinner
Use BODY 740 ACRYL THINNER



Non force dry –
10-16h / 22-25°C
20-30 min / 60-65°C
panel temperature

Solid Content (No thinner):
44% Weight

VOC (2004/42/EC)
This product is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 580 g/L. 2004/42/IIB(e)(840)580



Ready to spray:
14-16s
Cup 4/23°C
DIN 53211@23°C



Short wave 8-10 min

Theoretical Coverage:
7-8 m² / l at 50micron dry film thickness



Compliant Spray gun
1.3 – 1.5 mm
3-4 bar inlet pressure
2x coats = 50-60 micron



Always wear protective equipment

Cleaning of equipment:
Clean after final use with Body 740 ACRYL NORMAL



HVLP 1.3 - 1.4mm
0.7 bar atomization pressure
2x coats = 50-60 micron



Follow the application instructions mentioned in this TDS

2K paint systems tend to react with water, hence all the equipment used must be moisture free. Isocyanates may cause skin sensitization. More specifically, care should be taken when handling the material. Anyone with a history of histaminic conditions, or respiratory problems should consult the doctor first.

For professional use only. The information displayed on this sheet has been carefully selected though a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.