



# BODY P 962 1K ISOLATOR

Technical Data Sheet No 130

VOC compliant with the regulations

One component air drying system

New generation primer suitable for metallic and wooden surfaces

Dries quickly

## General Technical Description



Non force dry –  
1h / 23°C

## Surface

Adhesion to any coated surface

## Pretreatment / Cleaning of substrate



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL / BODY 771 ANTISIL FAST.

Use P 400 for wet sanding, re-clean the surface and dry thoroughly.

Use P 180 for sanding on applications direct to metals



Make sure you always use appropriate face protection and good ventilation

**Product Application:** »» Apply 1 coat on any coated surface. Make sure there is a uniform coverage on the applied surface. 10-15 minutes between coats if necessary.



1K P 962 ISOLATOR is ready for use.



BODY 1K P962 ISOLATOR SHOULD NOT BE SANDED BEFORE THE APPLICATION OF ANY OTHER COATS OF PAINT

**Flash Point:**  
15°C / 59°F

### Remarks:

- Do not apply at temperatures below +5°C
- It can be used by countries that do not adopt the VOC legislation as well.
- Store in a cool place and use within 12 months for best results. Guaranteed shelf life of 24 months in unused original containers
- Clean all the equipment with any alcohol based solvents such as Body 796 Gun Wash Cleaner, in order to avoid any product remains in the spray gun
- Make sure you stir well and filter the product before every use. Do NOT overload, P962 ISOLATOR when applying. Always check that the air line is free of moisture.



Ready to spray:  
25-30 s - Cup 4 @23°C  
- DIN 53211



Over coat with:  
HB BODY PRIMERS  
HB BODY BASECOAT  
HB BODY AUTOEMAIL  
2K ACRYLIC PAINT

**Specific Gravity:**  
1.18 g/cm<sup>3</sup>

**Solid Content (No thinner):**  
50% Weight



Do not add thinner (Reducer)



Store in a cool place



HVLP Spray gun  
1.4m-1.8 mm  
0.7 bar atomization pressure  
1 coats = 10-20 micron (recommended)



Always wear protective equipment

### VOC (2001/42/EC)

This product is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 540 g/L. The VOC content in the ready for use form of this product is 535 g/L.  
2004/42/IB(c)(540)535

**Theoretical Coverage:**  
8-10 m<sup>2</sup> / l at 10 micron dry film



Allow 10-15 minutes between coats (if second coat is needed)



Follow the application instructions mentioned in this TDS

**Cleaning of equipment:**  
Clean after final use with Body 769 Gun wash Cleaner



Non force dry –  
1 h / 23°C

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

Issue 1/2013, October 2013