



SPRAY BODY Waterborne Prefill

Technical Data Sheet No 815

VOC compliant with the regulations

It is compatible with all type of paints and primers based in water

It can be compatible with: 1K topcoats, metallic effect paints, 1K primers, 1K waterborne clear coats

Contains universal thinner and propellant gas

General Technical Description

2-3 passes

Dust free 10-12 mins at 18-22 °C

Surface

On old, sanded paint work

Metal or wooden surfaces

OEM surfaces

Clean and sanded steel panels

HB Body Polyester Fillers

Pretreatment / Cleaning of substrate



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL / BODY 771 ANTISIL FAST.

Make sure the surface is air dried rather than wiped dry



Make sure you always use appropriate face protection and good ventilation

Product Application: »» It can be compatible with all water based products: 1K topcoats, metallic effect paints, 1K primers, 1K waterborne clear coats. For 1K topcoats and primers as well as metallic effect paints you need to fill 100 ml.



Shake well before using

Flash Point:
-97°C

Specific Gravity:
0.70 g/cm³

Solid Content (No thinner):
-

VOC (2001/42/EC)

This product is an aerosol product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 720g/L. 2004/42/IIIB(e)(840)720

Theoretical Coverage:
-

Cleaning of equipment:
-

Remarks:

- Always try to use the product in accordance with the specifications provided.
 - It can be used by countries that do not adopt the VOC legislation as well.
 - Shake thoroughly before use.
 - Shake for 1-2 mins after agitator ball has started to rattle.
- After preparing the area to be painted ensure it to be free from dirt, wax, oil etc. Test on a similar surface using a back and forth action.
- Optimum operating temperature range 10-25°C.

Storage shelf life:

Store in a cool place and use within 36 months for best results. Guaranteed shelf life of 36 months in unused original containers



2-3 coats approximately 20-30 microns



Dust free 10-12 mins at 18-22 °C



Full hardness within 24 hours.

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

Issue 1/2013, April 2013