

260 POLYESTER SPRAY FILLER

Technical Data Sheet No 503



General Technical Description

2K polyester-based Spray Filler

Ideal for filling of rough surface areas

Easily applied, by spray gun

Surface

Metallic surfaces
-Aluminium
-Stainless steel
-Bare metal

Pretreatment / Cleaning of substrate



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL / 771 ANTISIL FAST DEGREASER.

Make sure the surface is first wiped dry and then air dried



Make sure you always use appropriate face protection and good ventilation

Product Application: Apply with a spray gun when mixed with hardener directly on metallic, surfaces



Mix 100 parts 260 BODY FILLER with 5 parts BODY HARDENER



P120- P240

Flash Point:
17°C / 63°F

Specific Gravity:
1.40g/cm³

Remarks:

- Application only with Body Hardener. Mix well with putty. Do not add more than 5% as this may cause staining of the topcoat finish.
- Avoid other thinners (e.g. NITRO THINNER).
- Do not apply to Etch Primer, 1K Filler, TPA substrates and soft old paintwork.
- Do not apply at temperatures below +5°C (+41°F)
- It can be used by countries that do not adopt the VOC legislation as well.
- In temperature above 80 - 100°C (176 - 212°F) reduce the quantity of hardener by 50% to avoid the possibility of peeling.



5-10% BODY POLY 780 POLYESTER THINNER



Store in a cool place

Solid Content (No thinner):
72% Weight

VOC (2004/42/EC)

This product is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 540g/L. The VOC content in the ready for use form of this product is 240 g/L. 2004/42/IIB(b)(540)240

Storage shelf life:

- Polyester materials have a limited shelf life. Store in a cool place +5°C - +25°C (+41°F - +77°F) and use within 12 months for best results. Guaranteed shelf life of 12 months in unused original containers.



Ready for use
30s
DIN 6 @ 23 °C (73°F)



Always wear protective equipment

Theoretical Coverage:

-

Cleaning of equipment:
Clean after final use with ECO THINN 767
NITRO THINNER



Gravity feed spray gun: 2.5 – 3 mm
3-5 bar inlet pressure



Follow the application instructions mentioned in this TDS



Non force dry
2-3h /23°C (73°F)
30min/60°C (140°F)
panel temperature



Short wave 6 – 10 min
Lamp distance: 60-70cm

Hardener bottle contains organic peroxide and is an oxidant. If hardener comes in contact with the skin, wipe off immediately and wash with soap and water. After eye contact irrigate copiously with water and seek medical advice immediately.

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.