



**TECHNICAL DATA SHEET No 701** 

# **BODY 650 STONE CHIP**

### **GENERAL TECHNICAL DESCRIPTION**

Synthetic rubber-based underbody material with sound deadening / sealing properties and optimum covering ability

Protection from stone chips and rust

Excellent adhesion, quick drying

It can be painted over with all HB BODY Mix Systems

Ready for use

# **PRODUCT APPLICATION**



Shake well before using: 2 - 3 min

Apply with UBS gun Pressure: 5 - 6 bar (73 - 87 psi) 150 - 200 µm (5.9 - 7.9 mil)

SURFACE

parts of the car body

External underneath and internal



5 - 10 min / 23°C (73°F) Flash off time

ŧ	( (
	1

PRETREATMENT/CLEANING OF SUBSTRATE

Clean substrate using a soft cloth and 770 ANTISIL NORMAL / 771

ANTISIL FAST DEGREASER.

Make sure the surface is first wiped dry

and then air dried.

Use 340 PLASTOFIX (Recommended) Compliant Spray gun 1.3 – 1.5 mm 1x coat = 10 - 15 micron (0.4 - 0.6mil)

	$\overline{)}$	)	)+
1.55.51.6.5	<u> </u>	(	()

# 5 - 10 min / 23°C (73°F) Final flash off time

It can be painted over with all HB BODY Mix Systems



Non force dry 2 h / 23°C (73°F) 30 min / 60°C (140°F) panel temperature

### **STORAGE SHELF LIFE**

 Store in a cool place (+5°C - +25°C) (41°F - 77°F) and use within 12 months for best results. Guaranteed shelf life of 24 months in unused original containers



Always wear protective equipment

|--|

Follow the application instructions mentioned in this TDS

**FLASH POINT** 9°C / 48°F

SPECIFIC GRAVITY 1.5 g/cm<sup>3</sup>

SOLID CONTENT (NO THINNER) 75% Weight

## VOC (2004/42/EC)

This product is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 840 g/L 2004/42/IIB(c)(840)840

### THEORETICAL COVERAGE

5 - 6 m<sup>2</sup> / I at 100 micron (4 mil) dry film thickness

**CLEANING OF EQUIPMENT** 

Clean after final use with 767 NITRO THINNER

# REMARKS

• It can be also spread by brush to give form and texture

· Allow for additional time for combi spray booths to reach the desired temperature Best results when used with HB BODY

products

