



TECHNICAL DATA SHEET No 217

BODY 697 CLEAR HS SR 2:1

GENERAL TECHNICAL DESCRIPTION

Fast hardening, high solid clear coat suitable for full body, partial or spot panel repairs
High mechanical and chemical resistance
Excellent leveling and gloss retaining

SURFACE

HB BODY Color Solutions Basecoat Mix System
HB BODY Color Solutions 2K Acrylic Mix System
HB BODY Color Solutions Aqua Basecoat Mix System

PRETREATMENT/CLEANING OF SUBSTRATE



Clean substrate using a soft cloth and 770 ANTISIL NORMAL / 771 ANTISIL FAST DEGREASER.

Make sure the surface is first wiped dry and then air dried.

PRODUCT APPLICATION:



Mix 2 parts CLEAR COAT with 1 part BODY 620 HARDENER or H 752 SLOW / H 753 NORMAL / H 754 FAST HARDENERS FOR TOPCOATS
Pot life: > 7 h / 23°C (73°F)



Addition 0 - 5% 740 NORMAL / 741 SLOW ACRYL THINNER/REDUCER



Ready to spray: 13 - 16 s
DIN 4 / 20°C (68°F)



Compliant spray gun
1.3 - 1.4 mm
2 - 3 bar (29 - 44 psi)
2x coats = 50 - 60 µm
(2 - 2.4 mil)



1.2 - 1.3 mm
2 bar (29 psi)
2x coats = 50 - 60 µm
(2 - 2.4 mil)



5 - 10 min / 23°C (73°F)
Flash off time



8 - 14 hrs / 23°C (73°F)
20 - 30 min / 60°C (140°F)
panel temperature



Short wave 8 - 10 min
Distance: 60 - 70 cm

FLASH POINT

24°C / 75°F

SPECIFIC GRAVITY

0.95 g/cm³

SOLID CONTENT

(NO THINNER)

43% Weight

VOC (2004/42/EC)

This product is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 840 g/L. The VOC content in the ready for use form of this product is 840 g/L. 2004/42/IIIB(e) (840)840

CLEANING OF EQUIPMENT

Clean after final use with 740 ACRYL NORMAL thinner / reducer

REMARKS

- Allow for additional time for combi spray booths to reach the desired temperature
- Application only with the recommended hardeners and solvents
- Do not use at temperatures below 10°C (50°F)

STORAGE SHELF LIFE

- Store in a cool place +5°C - +25°C (+40 - +77°F) and use within 12 months for best results. Guaranteed shelf life of 24 months in unused original containers



Always wear protective equipment



Follow the application instructions mentioned in this TDS

2K paint systems tend to react with water, hence all the equipment used must be moisture free. Isocyanates may cause skin sensitization. More specifically, care should be taken when handling the material. Anyone with a history of histaminic conditions, or respiratory problems should consult the doctor first.

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

SEPTEMBER 2021